

Category	Grade	Br	Hcb	Hcj	(BH)Max
		Gs	Oe	Oe	MGOe
Isotropic Calendering	HM-7	1750-1850	1300-1400	2100-2300	0.65-0.75
Semi-anisotropic Extruding	HM-10	1800-1900	1500-1650	2200-2500	0.70-0.85
Semi-anisotropic Calendering	HM-10	1950-2100	1500-1600	2050-2250	0.85-1.0
Anisotropic Extruding	HM-256	1900-2000	1650-1850	2600-3200	0.90-1.10
Anisotropic Calendering	HM-256	2500-2600	2100-2300	2500-3000	1.50-1.60