

Grade	Br	Hcb	Hcj	(BH)Max	α (Br)
	MT	KA/M	KA/M	KJ/M ³	% / °C
	Gs	KOe	KOe	MGOe	
SCZ-4T	380-420	200-280	640-1030	28-36	-0.03
	3.8-4.2	2.5-3.5	8.0-13.0	3.5-4.5	
SCZ-5T	410-540	265-360	640-1200	36-44	-0.03
	4.1-5.4	3.3-4.5	8.0-15.0	4.5-5.5	
SCZ-9	610-660	415-480	640-1200	68-76	-0.03
	6.1-6.6	5.2-6.0	9.0-15.0	8.5-9.5	
SCZ-11	640-720	430-510	640-1200	76-88	-0.03
	6.4-7.2	5.4-6.4.4	8.0-15.0	9.5-11.0	

Note: T is an isotropic material.